



---

## INTRODUCTION TO SAMPLE SPECIFICATION – CONCRETE PROTECTION PRODUCTS

---

The following specification guideline reflects current industry installation procedures and GSE StudLiner quality control test procedures. This guideline is presented as a sample format to be used as a guide only in preparing project specific specification.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. GSE assumes no liability in connection with the use of this information. Please check with GSE for current, standard minimum quality assurance procedures and specifications.

GSE and other trademarks in this document are registered trademarks of GSE Lining Technology, Inc. in the United States and certain foreign countries.

# CONCRETE EMBEDMENT LINER

## PART 1: GENERAL

### 1.01 SECTION INCLUDES

- A. Specifications and guidelines for MANUFACTURING high-density polyethylene embedment liners.

### 1.02 REFERENCES

- A. American Society for Testing and Materials (ASTM)
  1. D 1505 Test Method for Density of Plastics by the Density-Gradient Technique
  2. D 1603 Test Method for Carbon Black in Olefin Plastics
  3. D 5199 Standard Test Method for Measuring Nominal Thickness of Geotextiles and Geomembranes
  4. D 5596 Standard Test Method for Microscopic Evaluation of the Dispersion of Carbon Black in Polyolefin Geosynthetics
  5. D 6693 Standard Test Method for Determining Tensile Properties of Nonreinforced Polyethylene and Nonreinforced Flexible Polypropylene Geomembranes
  6. D 1204 Standard Test Method for Linear Dimensional Changes of Nongrid Thermoplastic Sheeting or Film at Elevated Temperature
  7. D 696 Standard Test Method for Coefficient of Linear Thermal Expansion of Plastics Between -30°C and 30°C With a Vitreous Silica Dilatometer
  8. D 746 Standard Test Method for Brittleness Temperature of Plastics and Elastomers by Impact
  9. D 570 Standard Test Method for Water Absorption of Plastics
  10. E 96 Standard Test Method for Water Vapor Transmission of Material

### 1.03 POST AWARD AND SUBMITTALS

- A. All work for and in connection with the installation of the lining, field seaming and welding joints shall be completed in strict conformity with all applicable instructions and recommendations of the liner manufacturer.
- B. All surfaces in contact with corrosive or erosive environments or environments susceptible to mechanical damage shall be lined with GSE StudLiner as manufactured by GSE Lining Technology, Inc.
- C. At the request of the Engineer, Pre-Caster or End User, samples, datasheets, installation instructions, etc will be provided.
- D. Included with the shipment of liner, submit certified test reports that the liner and material are manufactured in accordance with standards specified herein.

### 1.04 QUALIFICATIONS

- A. The HDPE liner specified in this section shall be furnished by a manufacturer who is

fully experienced, reputable and qualified in the manufacturing of the materials. The manufacturer must at least 10 years of manufacturing experience.

- B. Locking devices must be extruded to the sheet as a one step process.
- C. Liner shall be GSE StudLiner as manufactured by GSE Lining Technology, Inc.
- D. Liner shall be produced in the United States.
- E. Liner shall be 8 feet in width.
- F. Liner shall demonstrate a minimum pull-out strength of 14,000 psf.

## PART 2: PRODUCT

### 2.01 ROLL DIMENSIONS

- A. Embedment sheets shall be produced in rolls that are 8.0 ft (2.4 m) in width and a thickness range of 80 mils (2.0 mm) to 200 mils (5.0 mm) in thickness. Roll lengths vary according to thickness.
- B. Locking studs of the same material as that of the liner shall be integrally extruded with the sheet. Stud spacing shall be on approximate 1.25 in (30 mm) centers, such that there are approximately 110 studs per square foot (1200 per square meter).

### 2.02 MATERIAL PROPERTIES

- A. The material used in the embedment liner and in all welding strips shall be made from 97-98% virgin high density polyethylene and 1.5-3% carbon black or pigmentation for the purpose of an otherwise specified color.
- B. Plasticizer shall not be added to the resin formulation.
- C. Embedment sheet and welding strips shall be free of holes, pinholes, bubbles, blisters, excessive contamination by foreign matter, and nicks and cuts on roll edges.
- D. The HDPE cap strips shall be made from HDPE, have good impact resistance and have an elongation sufficient to bridge up to 1/4 inch settling cracks.
- E. Cap strips shall be approximately 4 inches wide or greater and shall be equivalent to that of the liner.
- F. Material shall maintain a repairable state through it's lifecycle by methods approved and recommended by the manufacturer.
- G. Embedment sheets shall have the following physical properties when tested in accordance with Table 1.
- H. Raw resin shall have the following properties when tested in accordance with Table 2.

**Table 1: Material Properties**

Property	Test Method	Nominal Value				Testing Frequency
		2.00 (80)	3.00 (120)	4.00 (160)	5.00 (200)	
Thickness, mm (mil)	ASTM D 5199	2.00 (80)	3.00 (120)	4.00 (160)	5.00 (200)	Every 5 <sup>th</sup> roll
Density, g/cm <sup>3</sup>	ASTM D 1505	0.94	0.94	0.94	0.94	1/100,000 ft <sup>2</sup>
Tensile Properties	ASTM D 6693					
Strength@Yield,lb/in <sup>2</sup> (MPa)	Type IV, Dumbbell G.L.= 2.0in (50 mm)	2,200 (14.5)	2,200 (14.5)	2,200 (14.5)	2,200 (14.5)	1/100,000 ft <sup>2</sup>
Elongation @ Break, %		500	500	500	500	
Stud Pull-Out Strength <sup>1</sup> , lb/ft <sup>2</sup> (kN/m <sup>2</sup> )		>14,000 (669.89)	>14,000 (669.89)	>14,000 (669.89)	>14,000 (669.89)	1/ product
Carbon Black Content/ Pigment Content, %						1/100,000 ft <sup>2</sup>
Black Liner	ASTM D 1603, mod.	2-3	2-3	2-3	2-3	
Gray Liner	ASTM D 5630, mod.	1.5 – 2.5	1.5 – 2.5	1.5 – 2.5	1.5 – 2.5	
Carbon Black Dispersion <sup>2</sup>	ASTM D 5596	Note 2	Note 2	Note 2	Note 2	1/100,000 ft <sup>2</sup>
Notched Constant Tensile Load, hours	ASTM D 5397	400	400	400	400	1/ formulation
Coefficient of Linear Thermal Expansion, per °C	ASTM D 696	1.20E-04	1.20E-04	1.20E-04	1.20E-04	1/ product
Low Temperature Brittleness, °C	ASTM D 746	-77	-77	-77	-77	1/ product
Dimensional Stability, % (each direction)	ASTM D 1204	± 1.0	± 1.0	± 1.0	± 1.0	1/ product
Water Absorption, %	ASTM D 570	0.1	0.1	0.1	0.1	1/ product
Water Vapor Transmission, (g/m <sup>2</sup> /day)	ASTM E 96	<0.01	<0.01	<0.01	<0.01	1/ product

<sup>1</sup>Note: Concrete must have a compressive strength of at least 5,000 lb/in<sup>2</sup> (34,500 kPa).

<sup>2</sup>Note: Dispersion only applies to near spherical agglomerates. 9 of 10 views shall be Category 1 or 2. No more than 1 view for category 3.

**Table 2: Raw Material Properties**

Property	Test Method	Value	Testing Frequency
Density, g/cm <sup>3</sup>	ASTM D 1505	0.932	1/ resin lot
Melt Flow, g/10 min	ASTM D 1238 (190/2.16)	≤ 1.0	1/ resin lot
OIT, minutes	ASTM D 3895 (1atm/200°C)	100	1/ formulation

## 2.03 MATERIAL SUPPLY

- A. Embedment sheets shall be supplied in roll form, sheets, pre-fabricated tubes or panels.
- B. Cap strips shall be supplied in 4 inch widths or greater.

## 2.04 MATERIAL HANDLING AND STORAGE

- A. Materials are to be handled as to prevent damage.
- B. The on-site storage location for geomembrane material, provided by the CONTRACTOR to protect the liner from punctures, abrasions and excessive dirt and moisture. Storage area should have the following characteristics:
  1. level (no wooden pallets)
  2. smooth
  3. dry
  4. protected from theft and vandalism