

GSE FabriNet HF Geocomposite

GSE FabriNet HF geocomposite consists of a 250 mil thick GSE HyperNet HF geonet heat-laminated on one or both sides with a GSE nonwoven needle-punched geotextile. The geotextile is available in mass per unit area range of 6 oz/yd² to 16 oz/yd². The geocomposite is designed and formulated to perform drainage function under a range of anticipated site loads, gradients and boundary conditions.



AT THE CORE:
A 250 mil thick GSE HyperNet HF geonet heat-laminated on one or both sides with a nonwoven needle-punched geotextile.

Product Specifications

Tested Property	Test Method	Frequency	Minimum Average Roll Value		
Geocomposite			6 oz/yd ²	8 oz/yd ²	10 oz/yd ²
Transmissivity ⁽²⁾ , gal/min/ft (m ² /sec) Double-Sided Composite Single-Sided Composite	ASTM D 4716	1/540,000 ft ²	2.4 (5 x 10 ⁻⁴) 7.2 (1.5 x 10 ⁻³)	2.4 (5 x 10 ⁻⁴) 7.2 (1.5 x 10 ⁻³)	1.4 (3 x 10 ⁻⁴) 4.8 (1 x 10 ⁻³)
Ply Adhesion, lb/in	ASTM D 7005	1/50,000 ft ²	1.0	1.0	1.0
Geonet Core⁽³⁾ - GSE HyperNet HF					
Transmissivity ⁽²⁾ , gal/min/ft (m ² /sec)	ASTM D 4716		14.5 (3 x 10 ⁻³)	14.5 (3 x 10 ⁻³)	14.5 (3 x 10 ⁻³)
Density, g/cm ³	ASTM D 1505	1/50,000 ft ²	0.94	0.94	0.94
Tensile Strength (MD), lb/in	ASTM D 5035/7179	1/50,000 ft ²	55	55	55
Carbon Black Content, %	ASTM D 1603 ⁽⁶⁾ /4218	1/50,000 ft ²	2.0	2.0	2.0
Geotextile^(3,4)					
Mass per Unit Area, oz/yd ²	ASTM D 5261	1/90,000 ft ²	6	8	10
Grab Tensile, lb	ASTM D 4632	1/90,000 ft ²	160	220	260
Puncture Strength, lb	ASTM D 4833	1/90,000 ft ²	90	120	165
AOS, US sieve ⁽¹⁾ (mm)	ASTM D 4751	1/540,000 ft ²	70 (0.212)	80 (0.180)	100 (0.150)
Permittivity, sec ⁻¹	ASTM D 4491	1/540,000 ft ²	1.5	1.3	1.0
Flow Rate, gpm/ft ²	ASTM D 4491	1/540,000 ft ²	110	95	75
UV Resistance, % retained	ASTM D 4355 (after 500 hours)	per formulation	70	70	70
NOMINAL ROLL DIMENSIONS					
Geonet Core Thickness, mil	ASTM D 5199	1/50,000 ft ²	250	250	250
Roll Width ⁽⁵⁾ , ft			15	15	15
Roll Length ⁽⁵⁾ , ft	Double-Sided Composite Single-Sided Composite		230 260	210 260	210 250
Roll Area, ft ²	Double-Sided Composite Single-Sided Composite		3,450 3,900	3,150 3,900	3,150 3,750

[Product specifications continued on back]



AT THE CORE:

A 250 mil thick HyperNet HF geonet heat-laminated on one or both sides with a nonwoven needlepunched geotextile.

Product Specifications [continued]

NOTES:

- ⁽¹⁾AOS in mm is a maximum average roll value.
- ⁽²⁾Gradient of 0.1, normal load of 10,000 psf, water at 70°F between steel plates for 15 minutes. Contact GSE for performance transmissivity value for use in design.
- ⁽³⁾Component properties prior to lamination.
- ⁽⁴⁾Refer to geotextile product data sheet for additional specifications.
- ⁽⁵⁾Roll widths and lengths have a tolerance of ±1%.
- ⁽⁶⁾Modified.

GSE is a leading manufacturer and marketer of geosynthetic lining products and services. We've built a reputation of reliability through our dedication to providing consistency of product, price and protection to our global customers.

Our commitment to innovation, our focus on quality and our industry expertise allow us the flexibility to collaborate with our clients to develop a custom, purpose-fit solution.



[DURABILITY RUNS DEEP] For more information on this product and others, please visit us at GSEworld.com, call 800.435.2008 or contact your local sales office.